



MATERIAL

Identification	Plasmek wall product	Mfg By	Plasmek Products Oy, Heikki Kortelainen, Finland
Description	Wall material		

TEST EQUIPMENT

Type	Small flame, droplets test	Manufacture	FTT, Fire Testing Technology Ltd.
------	----------------------------	-------------	-----------------------------------

PROCEDURE

Standard	ISO 11925-1	Method	Surface or edge ignition	Rating	D0/not pass
----------	-------------	--------	--------------------------	--------	-------------

End point of Test	Time exceeds 60 sek.
-------------------	----------------------

Specimen	Method	Qualification	Conditioned			Testing date	Sample size:
			Temp	Humidity	Hours		
1	Surface ignition	D0	25	50	168	8/28/17	13 x 125 x 10 mm
2	Surface ignition	D0	25	50	168	8/28/17	13 x 125 x 10 mm
3	Surface ignition	D0	25	50	168	8/28/17	13 x 125 x 10 mm
4	Surface ignition	D0	25	50	168	8/28/17	13 x 125 x 10 mm
5	Surface ignition	D0	25	50	168	8/28/17	13 x 125 x 10 mm
6	Surface ignition	D0	25	50	168	8/28/17	45 x 250 x 10 mm
7	Surface ignition	D0	25	50	168	8/28/17	45 x 250 x 10 mm

Material result No burning droplets occurred

8/30/17
DATE

Kalle Kiviranta
SIGNATURE